VGS A4






FULL THREAD CONNECTOR WITH COUNTERSUNK HEAD

A4 | AISI316

A4 | AISI316 austenitic stainless steel for high corrosion resistance. Ideal for environments adjacent to the sea in corrosivity class C5 and for insertion on the most aggressive timbers in class T5.

T5 TIMBER CORROSIVITY

Suitable for use in applications on agressive woods with an acidity (pH) level below 4 such as oak, Douglas fir and chestnut, and in wood moisture conditions above 20%.




METAL-to-TIMBER recommended use:











A4 | AISI316 austenitic stainless



- timber based panels
- solid timber and glulam

steel (CRC III)

- CLT and LVL
- ACQ, CCA treated timber



CODES AND DIMENSIONS

d_1	CODE	L	b	pcs	
[mm]		[mm]	[mm]		
9 TX 40	VGS9120A4	120	110	25	
	VGS9160A4	160	150	25	
	VGS9200A4	200	190	25	Public proper
	VGS9240A4	240	230	25	
	VGS9280A4	280	270	25	_
	VGS9320A4	320	310	25	
	VGS9360A4	360	350	25	
11 TX 50	VGS11100A4	100	90	25	
	VGS11150A4	150	140	25	
	VGS11200A4	200	190	25	Puri propor
	VGS11250A4	250	240	25	
	VGS11300A4	300	290	25	
	VGS11350A4	350	340	25	
	VGS11400A4	400	390	25	
	VGS11500A4	500	500 490 25		-
	VGS11600A4	600	590	25	

RELATED PRODUCTS



HUS A4 TURNED WASHER

page 68



JIG VGZ 45°

TEMPLATE FOR 45° SCREWS

page 409




TORQUE LIMITER

TORQUE LIMITER

page 408

GEOMETRY



A G 2 M B				
L ≤ 240 mm				
VGS Ø11				
L ≤ 250 mm				

Vice do



250 mm < L ≤ 600 mm

Nominal diameter	d_1	[mm]	9	11
Head diameter	d_K	[mm]	16,00	19,30
Head thickness	t_1	[mm]	6,50	8,20
Thread diameter	d ₂	[mm]	5,90	6,60
Pre-drilling hole diameter ⁽¹⁾	$d_{V.S}$	[mm]	5,0	6,0

⁽¹⁾ Pre-drilling valid for softwood.

For the mechanical parameters please see ETA-11/0030.



HYBRID STEEL-TIMBER STRUCTURES

Ideal for steel structures where high-strength customised connections are required, particularly in adverse climatic contexts such as the marine environment and acidic woods.

SWELLING OF TIMBER

Application in combination with polymeric interlayers such as XYLOFON WASHER gives the joint a certain adaptability to mitigate stresses resulting from shrinkage/swelling of the wood.